

IKONOS PROFIFLEX DECO FPT P80 AIR+

PRODUCT DESCRIPTION:

Ikonos Profiflex Deco FPT P80 AIR+ is a silver, polymeric decorative film with frosted effect. Very simple to apply thanks to Fast & Easy technology, which allows to remove air bubbles during dry application. Recommended for any flat and transparent surfaces such as windows, shop windows, glass doors, mirrors, etc.

FPT P80 AIR+ meets the requirements of B-s1, d0 class according to PN-EN 13501-1 (classification of the reaction to fire performance).

PRODUCT STRUCTURE:

Film: 80 mic, polymeric, silver PVC film with frosted effect

Adhesive: permanent, transparent, water-based dispersion of polyacrylate

Liner: one-side siliconized, 140 gsm, structured, PCK type backing paper

RANGE OF APPLICATION:

Ikonos Profiflex Deco FPT P80 AIR+ was designed for long-term premium decoration purposes. It can be easily applied on glass or other flat and transparent surfaces in order to reach frosted effect.

PHYSICAL FEATURES:

	STANDARD NO.	VALUE
Thickness		
Thickness of PVC	ISO 2286-3	80 mic (±5%)
Total thickness	ISO 2286-3	260 mic (±5%)
Tensile stress at break	ISO 527-3/2/200	min. 20 MPa [MD]
Tensile strain at break	ISO 527-3/2/200	min. 160 % [MD]
Gloss level	DIN 67530, 85°	15 GU
Dimensional stability	DIN 53377	max. -2.8 %
Transmittance	ASTM D1003	73%
Haze	ASTM D1003	95.6%
Clarity	ASTM D1003	4.7 %
Adhesive Power		
Initial	FINAT 9	8.8 N/25 mm
After 20 min	FINAT 1	13.3 N/25 mm
After 24 h	FINAT 1	19.8 N/25 mm
Temperature range		
While applying	-	from 12°C to 25°C
While exploiting	-	from -20°C to 50°C
Durability		
	90° vertical exposure	indoor up to 7 years (unprocessed)
	90° vertical exposure	outdoor up to 4 years (unprocessed)
Shelf Life	2 years (in original packaging, at 20 °C and 50% relative humidity)	

* Producer's internal test method

DURABILITY

The data concerns vertical surface exposure of an unprinted/unprocessed film. The outdoor durability relates to the temperate climate of Middle Europe. If the film is exposed to extreme weather conditions, such as austere insolation, high UV radiation or humidity it may undergo accelerated deterioration. PVC film may also weaken in greatly contaminated areas and regions of high altitude.

HANDLING & PROCESSING

Recommended storage conditions: 50% of relative humidity, 20 oC, in original packaging.

Customer should always store rolls together with label which consist information about type of product, dimensions of roll and batch number.

Any claims or requests will not be accepted without information about batch number.

During storage time shrinking of the edges of monomeric PVC film could be noticed.

To obtain good print quality/good processing results we recommend acclimatize rolls in printing/processing room min. 24 hour before printing/processing. Large fluctuations in temperature and humidity between the room and the material have an impact on flatness and printability of material.

If printed, the ink must be perfectly dry before further processing e.g laminating or application. Features of products could be changed by the residuals solvents. The surface on which product is applied must be free of dust, grease, lubricant and any other substances which may hinder the film from adhesion.

Due to wide range of possible uses and applications customers should independently verify the appropriateness of material for their explicit purpose, prior to use. We strongly recommend customers conduct own tests before each application.

IMPORTANT NOTICE

The information included in the present publication is based upon our knowledge as well as practical experience and can be changed without prior notice. All information always represents an average, a minimum or maximum value and should be considered as such.

This data is displayed only in order to serve as a source of information and is given without guarantee and does not constitute a warranty.

All presented information refers to unprinted/unprocessed Ikonos products. Features of products could change after printing/processing due to this reason all printed/processed Ikonos products are not covered by warranty.

Our limited liability relates only to the cost of the defective material which was bought by customer.

Agents, representatives and salesmans are not entitled to give any guarantee, warranty or representation other to the foregoing.

Ikonos shall not be held responsible for any damage to substrates, surfaces or machines resulting from the use or removal of Ikonos product, nor shall Ikonos be held responsible for any consequential damage.

All Ikonos products sold are subject to "General conditions of sales and delivery" (<http://www.ikonos.pl/download-page>).

Ikonos shall not be held responsible for any incidental or consequential damage, including, but not limited to, loss of profit or income, labour cost, costs or expenses for reproducing graphics, loss of production time, costs for removing defective graphics, etc.

All rights reserved. All trademarks and registered trademarks are the property of their respective owners. August 2016.